



SKAMOL V-1100 (375) vermiculite insulating board
for back-up insulation up to 1100°C (2012°F)



Grade	V-1100 (375)	
Maximum service temperature		
	°C	1100
	°F	2012
Bulk density, dry		
	kg/m ³	375
	lbs/cu.ft.	23.4
Compressive strength (EN 1094-5: 1995)		
@ room temperature	MPa	1.3
	lbs/sq.in.	189
Modulus of rupture (EN 993-6: 1995)		
	MPa	0.5
	lbs/sq.in.	73
Total porosity		
	%	85
Specific heat		
	kJ/(kg×K)	0.94
	BTU/(lb×°F)	0.224
Coefficient of reversible thermal expansion (BS 1902: section 5.3: 1990)		
@ 20°C-750°C (68°F-1382°F)	K ⁻¹	11×10 ⁻⁶
	°F ⁻¹	6.1×10 ⁻⁶
Resistance to thermal shock (EN 993-11: 1998)		
heating to 950°C (1742°F)	cycles	>20
Linear reheat shrinkage (EN 1094-6: 1999)		
12 h at 1000°C (1832°F)	%	1.0
12 h at 1100°C (2012°F)		-
Pyrometric cone equivalent (ASTM C24-89 ORTON cones)		
	°C	1300
	°F	2372
Thermal conductivity (ASTM C-182)		
mean temp. @ 200°C	W/(m×K)	0.12
@ 400°C		0.15
@ 600°C		0.16
@ 800°C		0.19
@ 392°F	BTU/(sq.ft.×h×°F/in)	0.83
@ 752°F		1.04
@ 1112°F		1.11
@ 1472°F		1.32
Chemical analysis, typical		
	%	
Silica	SiO ₂	46
Titanium dioxide	TiO ₂	0.7
Ferric oxide	Fe ₂ O ₃	5.5
Alumina	Al ₂ O ₃	7.0
Magnesium oxide	MgO	19
Calcium oxide	CaO	3.5
Sodium oxide	Na ₂ O	0.2
Potassium oxide	K ₂ O	10
Loss on ignition 1025°C (1877°F)	LOI	7.0
Colour		SAND
HS Tariff number		
(Harmonized Commodity Description and Coding System)		6806.90.00

Skamol A/S
Østergade 58-60
DK-7900 Nykøbing Mors
Denmark
Tel: +45 9772 1533
Fax: +45 9772 4975
insulation@skamol.dk

www.skamol.com

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

March 2011