

**SKAMOL Moler insulating brick HIPOROS**  
for back-up insulation - up to 900°C (1652°F)



Grade	HIPOROS	
<b>Maximum service temperature</b>		
	°C	900
	°F	1652
<b>Bulk density, dry</b>		
	kg/m <sup>3</sup>	570
	lbs/cu.ft.	36
<b>Cold crushing strength (EN 1094-5:1995)</b>		
@ room temperature	MPa	1.6
	lbs/sq.in.	232
<b>Modulus of rupture (EN 993-6:1995)</b>		
	MPa	0.5
	lbs/sq.in.	73
<b>Total porosity (EN 1094-4: 1995)</b>		
	%	76
<b>Permeability to air (BS EN 993-4: 1995)</b>		
	nPm	16.5
<b>Creep in compression (EN 993-9: 1997)</b>		
50 h at 100°C (180°F) below max. service temperature load 0.1 MPa (14.5 lbs/sq.in.)	%	1.5
<b>Specific heat</b>		
	kJ/(kg×K)	0.70
	BTU/(lb×°F)	0.17
<b>Coefficient of reversible thermal expansion (BS 1902: section 5.3: 1990)</b>		
@ 20°C-750°C (68°F-1382°F)	K <sup>-1</sup>	3.0x10 <sup>-6</sup>
	°F <sup>-1</sup>	1.6x10 <sup>-6</sup>
<b>Resistance to thermal shock (EN 993-11: 1998)</b>		
	cycles	> 30
<b>Linear reheat shrinkage (EN 1094-6: 1999)</b>		
	%	1.0
<b>Pyrometric cone equivalent (ASTM C24-89 ORTON cones)</b>		
	°C	1200
	°F	2192
<b>Thermal conductivity (ASTM C-182 supplemented by ASTM C-201)</b>		
mean temp. @ 200°C	W/(m×K)	0.12
@ 400°C		0.14
@ 600°C		0.16
@ 800°C		0.18
@ 392°F	BTU/(sq.ft×h×°F/in)	0.83
@ 752°F		0.97
@ 1112°F		1.11
@ 1472°F		1.25
<b>Chemical analysis, typical</b>		
	%	
Silica	SiO <sub>2</sub>	72
Titanium oxide	TiO <sub>2</sub>	0.7
Ferric oxide	Fe <sub>2</sub> O <sub>3</sub>	7.0
Alumina	Al <sub>2</sub> O <sub>3</sub>	8.0
Magnesium oxide	MgO	1.2
Calcium oxide	CaO	6.5
Sodium oxide	Na <sub>2</sub> O	0.4
Potassium oxide	K <sub>2</sub> O	1.5
Sulphur trioxide	SO <sub>3</sub>	1.2
Loss on ignition 1025°C (1877°F)	LOI	1.5
<b>Colour</b>		
		red
<b>HS Tariff number</b>		
(Harmonized Commodity Description and Coding System)		6901.00.00

Skamol A/S  
Østergade 58-60  
DK-7900 Nykøbing Mors  
Denmark  
Tel: +45 9772 1533  
Fax: +45 9772 4975  
insulation@skamol.dk

www.skamol.com

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

March 2011