



SICAL mortar

silicon carbide mortar for jointing of SICAL-78 bricks



Maximum service temperature		
	°C	1350
	°F	2462
Chemical analysis, typical (XRF)		
	%	
Silicon carbide	SiC	87
Silica	SiO ₂	5.0
Ferric oxide	Fe ₂ O ₃	1.0
Alumina	Al ₂ O ₃	3.0
Others		4.0
Grain size (DS 405.9 : 1978)		
> 0.4 mm (0.016")	%	0.2
< 0.074 mm (0.003")	%	60
Packaging		
Combined plastic and fibre bag, unit weight	kg	25
	lbs.	55
Storage life under dry conditions		
	%	12 months
Water usage		
		5 - 6.5 litres water to 25 kg dry mix
		1.3 - 1.7 US gal. water to 55 lbs. dry mix
Joint thickness (recommended)		
	mm	< 1.5
	inch	< 0.06
Colour		
		Grey

Skamol A/S
 Østergade 58-60
 DK-7900 Nykøbing Mors
 Denmark
 Tel: 45 9772 1533
 Fax: 45 9772 4975
 insulation@skamol.dk

Sales offices

Skamol Europe GmbH
 Düsseldorferstrasse 88
 D-40667 Meerbusch
 Germany
 Tel: +49 (0) 2132-13694 0
 Fax: +49 (0) 2132-13694 64

Skamol Americas, Inc.
 10100 Park Cedar Drive
 Suite 124
 Charlotte, NC 28210
 USA
 Tel: +1 (704) 544-1015
 Fax: +1 (704) 544-1239

www.skamol.com

The manufacturer, Tangshan Hexagon Silicon Carbide Co., Ltd., China, is certified according to ISO 9002 and approved supplier by Skamol A/S. Data are average results of tests conducted under standard procedures and are subject to variation. All data are supplied in good faith and are subject to change without notice. No warranty or guarantee is implied. Misprint and errors excepted.

Skamol A/S is DS/EN ISO 9001 certified.