

V-LITE (375) Vermiculite insulating bricks

for hot-face and back-up insulation - up to 1100°C (2012°F)



Maximum service temperature		
	°C	1100
	°F	2012
Bulk density, dry		
	kg/m ³	375
	lbs/cu.ft.	23.4
Compressive strength (EN 1094-5: 1995)		
@ room temperature	MPa	1.3
	lbs/sq.in.	189
Modulus of rupture (EN 993-6: 1995)		
	MPa	0.5
	lbs/sq.in.	73
Total porosity		
	%	86
Specific heat		
	kJ/(kg×K)	0.94
	BTU/(lb×°F)	0.224
Coefficient of reversible thermal expansion (BS 1902: section 5.3: 1990)		
@ 20°C-750°C (68°F-1382°F)	K ⁻¹	11×10 ⁻⁶
	°F ⁻¹	6.1×10 ⁻⁶
Resistance to thermal shock (EN 993-11: 1998)		
heating to 950°C (1742°F)	cycles	>10
Linear reheat shrinkage (EN 1094-6: 1999)		
	%	1.0
Pyrometric cone equivalent (ASTM C24-89 ORTON cones)		
	°C	1300
	°F	2372
Thermal conductivity (ASTM C-182 supplemented by ASTM C-201)		
mean temp. @ 200°C	W/(m×K)	0.12
mean temp. @ 400°C	W/(m×K)	0.14
mean temp. @ 600°C	W/(m×K)	0.16
mean temp. @ 392°F	BTU/(sq.ft.xh×°F/in.)	0.83
mean temp. @ 752°F	BTU/(sq.ft.xh×°F/in.)	0.97
mean temp. @ 1112°F	BTU/(sq.ft.xh×°F/in.)	1.11
Chemical analysis, typical	%	
Silica	SiO ₂	47
Titanium dioxide	TiO ₂	0.5
Ferric oxide	Fe ₂ O ₃	4
Alumina	Al ₂ O ₃	7
Magnesium oxide	MgO	21
Calcium oxide	CaO	2
Sodium oxide	Na ₂ O	0.5
Potassium oxide	K ₂ O	11
Loss on ignition 1025°C (1877°F)	LOI	7
Colour		Light brown

Skamol A/S
 Østergade 58-60
 DK-7900 Nykøbing Mors
 Denmark
 Tel: 45 9772 1533
 Fax: 45 9772 4975
 insulation@skamol.dk

Sales offices

Skamol Europe GmbH
 Düsseldorfstrasse 88
 D-40667 Meerbusch
 Germany
 Tel: +49 (0) 2132-13694 0
 Fax: +49 (0) 2132-13694 64

Skamol Americas, Inc.
 10100 Park Cedar Drive
 Suite 124
 Charlotte, NC 28210
 USA
 Tel: +1 (704) 544-1015
 Fax: +1 (704) 544-1239

www.skamol.com

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

Skamol A/S is DS/EN ISO 9001 certified.