

## V-LITE (475) Vermiculite insulating bricks

for hot-face and back-up insulation - up to 1100°C (2012°F)



Maximum service temperature		
	°C	1100
	°F	2012
Bulk density, dry		
	kg/m <sup>3</sup>	475
	lbs/cu.ft.	29.6
Compressive strength (EN 1094-5: 1995)		
@ room temperature	MPa	2.5
	lbs/sq.in.	363
Modulus of rupture (EN 993-6: 1995)		
	MPa	1.0
	lbs/sq.in.	145
Total porosity		
	%	81
Specific heat		
	kJ/(kg×K)	0.94
	BTU/(lb×°F)	0.224
Coefficient of reversible thermal expansion (BS 1902: section 5.3: 1990)		
@ 20°C-750°C (68°F-1382°F)	K <sup>-1</sup>	11×10 <sup>-6</sup>
	°F <sup>-1</sup>	6.1×10 <sup>-6</sup>
Resistance to thermal shock (EN 993-11: 1998)		
heating to 950°C (1742°F)	cycles	>10
Linear reheat shrinkage (EN 1094-6: 1999)		
	%	1.0
Pyrometric cone equivalent (ASTM C24-89 ORTON cones)		
	°C	1300
	°F	2372
Thermal conductivity (ASTM C-182 supplemented by ASTM C-201)		
mean temp. @ 200°C	W/(m×K)	0.14
mean temp. @ 400°C	W/(m×K)	0.16
mean temp. @ 600°C	W/(m×K)	0.19
mean temp. @ 392°F	BTU/(sq.ft.xh×°F/in.)	0.97
mean temp. @ 752°F	BTU/(sq.ft.xh×°F/in.)	1.11
mean temp. @ 1112°F	BTU/(sq.ft.xh×°F/in.)	1.32
Chemical analysis, typical	%	
Silica	SiO <sub>2</sub>	47
Titanium dioxide	TiO <sub>2</sub>	0.5
Ferric oxide	Fe <sub>2</sub> O <sub>3</sub>	4
Alumina	Al <sub>2</sub> O <sub>3</sub>	7
Magnesium oxide	MgO	21
Calcium oxide	CaO	2
Sodium oxide	Na <sub>2</sub> O	0.5
Potassium oxide	K <sub>2</sub> O	11
Loss on ignition 1025°C (1877°F)	LOI	7
Colour		Light brown

**Skamol A/S**  
 Østergade 58-60  
 DK-7900 Nykøbing Mors  
 Denmark  
 Tel: 45 9772 1533  
 Fax: 45 9772 4975  
 insulation@skamol.dk

**Sales offices**

**Skamol Europe GmbH**  
 Düsseldorfstrasse 88  
 D-40667 Meerbusch  
 Germany  
 Tel: +49 (0) 2132-13694 0  
 Fax: +49 (0) 2132-13694 64

**Skamol Americas, Inc.**  
 10100 Park Cedar Drive  
 Suite 124  
 Charlotte, NC 28210  
 USA  
 Tel: +1 (704) 544-1015  
 Fax: +1 (704) 544-1239

[www.skamol.com](http://www.skamol.com)

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

Skamol A/S is DS/EN ISO 9001 certified.