

Skamol^{Industry} Alu Bedding Mix HI

Grade		Value	Unit
Bulk density, average		495	g/L
Bulk density, maximum		540	g/L
Grain size			
	>6.3 mm	3	%
	3.15 to 6.3 mm	36	%
	1.0 to 3.15 mm	59	%
	0.5 to 1.0 mm	1.5	%
	<0.5 mm	0.5	%
Chemical analysis, typical			
Silica	SiO ₂	71	%
Titanium dioxide	TiO ₂	1.4	%
Ferric oxide	Fe ₂ O ₃	8.4	%
Alumina	Al ₂ O ₃	10.5	%
Magnesium oxide	MgO	1.6	%
Calcium oxide	CaO	2.5	%
Potassium oxide + Sodium oxide	K ₂ O + Na ₂ O	2.1	%
Other oxides		1.1	%
Colour		Red	

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted. Revision number: 13.1.2021