

Skamol Adhesive

	Value	Unit
Bulk density	≤ 1,600	kg/m ³
Compressive strength	CS IV	
Water absorption	Class W0	
Water vapour transmission, μ (EN 12086)	≤ 15	
Adhesion	≥ 0.08	N/mm ² FP B
Thermal conductivity, λ _{10 dry} (average tabular value; P=50%)	0.61	W/m×K

General		
Bag size	20	kg
Consumption (per bag)	5	m ²
Shelf life	12	months
Pouring temperature	+5 to +25	°C
Opening time at +20°C	60	minutes
Added water (per bag)	5	L

Classification reaction to fire (EN 13501-1:2007 + A1:2009)	Class A1	
HS Tariff number (Harmonized Commodity Description and Coding System)	2824.50.90	
Colour	Grey	



Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted. Revision number: 13.7.2022